

PPF Flu Orange

General

It is a PVC free and Phthalate free fluorescent printing paste

Advantages

- PPF Flu Orange is easily fixed.
- It doesn't contain phthalate and PVC. Suitable to ecological standards. Its curing time is at 320 °F / 160 °C for 1,5 mins.

Applications

- PPF Flu Orange allows which turns the requested color of printing paste
- To reduce the viscosity, PPF Thinner can be added [1-3 %] into PPF Base.
- Before use, please stir this product well. Do not use any additives that are not advised.
- After using, the screen should be cleaned with the synthetic thinner.

Usage

- PPF Flu Orange can be used to make alive colors,
- It can be mixed with PPF pigments.
- It is advised to print with the silk-screen that are made between 43-120 mesh [110-230 inch]
- 60-80 Shore, V type dr. blade should be used.

Storage & Shelf Life

- Keep containers dry and tightly closed. Store in a ventilated place between [+5]-[+30] °C/[+41]-[+86] ° F of temperature.
- It should be consumed within 2 years after the production date.

Important

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area.

The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.

Technical Details:



Appearance

Paste



Odor

Characteristic



Color

Fluorescent Orange



Viscosity

[[77 °F / 25°C] sp: 7, rpm: 2 Brookfield] : 1.000.000 - 1.100.000 [mPa.s]



Density

1,1 g/cm³ [25 °C/77°F]



Specific Gravity

.



pH

.



Boiling Point

>212°F [100°C]



Solubility

Dispersible in water



Explosion Hasard

It's not explosive



Packaging Information

PPF Flu Orange is packed in 1/5/10/20/30 Kg. cans.

[Standarts: for fastness tests - ISO 105-X10: 1993 / ISO 105-D01:2010 / ISO 105-B02:2013]