

WX Antimigration

General

It is a water based barrier printing base.

Advantages

- WX Antimigration is prevent to contaminate base color's to print.
- Especially WX Antimigration effective on polyester fabric and reactive printing fabric.
- WX Antimigration has extremely wash fastness.
- Curing temperature : 160°C(320°F), 1 min 30 seconds ; 140°C(284°F), 2 mins.
- Suitable to ecological standards

Applications

- WX Antimigration is used for prevent to contaminate prints of polyester fabric & reactive printing fabric.
- Before use, please stir WX Antimigration well.
- Do not use any additives that are not advised.

Usage

- It provides to print with the silk-screen that are made between 37-43 mesh.
- It can be fixed under room temperature.
- 55- 60 Shore, U type should used

Storage & Shelf Life

- Keep containers dry and tightly closed. Store in a ventilated place between (+5)-(+30)°C /(+41)-(+86)°F of temperature.
- It should be consumed within 2 years after the production date.

TECHNICAL DATA SHEET

Technical Details

| 0 | Appearance Paste |
|--------------------------|--|
| \bigcirc | Odor Characteristic |
| Ð | Color Dark Grey |
| Ø | Viscosity [(77°F/25°C) sp: 7, rpm: 20 Brookfield]: 50.000 – 65.000 [mPa.s] |
| 000 000 000 | Density 1,15 g/cm3 (68 °F / 20°C) |
| PH | pH 7,5 – 8,5 |
| | |
| ſ | Boiling Point >100°C (212°F) |
| ్ర ంర్గం | |
| <u>ව</u> ංූ්ට දුරු | >100°C (212°F) Solubility |

Important

The technical application and information that have been given above, are designed only as using instructions. Should not be considered as a warranty for any other use. When any help or assistance is required, our technical department is ready for help.

In case of emergency, Safety Data Sheet of this product should be ready for help at the working area. The warnings are given on safety data sheet of this product is for use outside the manufacturer/ distributor to direct/indirect can not be held responsible for any loss or damage.

Rev. DATE: 1 December 2021 Rev. No: 03

TDS No: 221 Page 1/1

Uras Kimya San. ve Tic. A.Ş Çobançeşme Mah. Sanayi Cad, Genç Osman 1 Sok No:14, 34196 Bahçelievler / İstanbul / Turkey +90 212 489 30 27 <u>uras@uraschemical.com</u>